



Technical Process Bulletin

Technical Process Bulletin No. 235110
 This Revision: 03-08-1990

ALODINE® 1201
 Brush or Immersion Application

1. Introduction:

ALODINE 1201 is a nonflammable, chromic acid based, coating chemical that will produce a chrome conversion coating on aluminum and its alloys.

The coating formed by ALODINE 1201 is gold to tan in color and it becomes a part of the aluminum surface. This chrome conversion coating offers the best affordable substrate for both paint adhesion and corrosion resistance.

2. Operating Summary:

<u>Brush Application:</u>	
Apply to a chemically cleaned surface using the solution undiluted from the container.	
<u>Immersion Application:</u>	
For each 100 parts of bath, mix 33 parts of ALODINE 1201 and 67 parts of water.	
<u>Operation and Control:</u>	
Time	2 to 5 minutes
Temperature	Ambient to 100° Fahrenheit

3. The Process:

The process to prepare metal for painting normally consists of the following steps:

- A. Cleaning (ALUMIPREP® 33, Technical Process Bulletin No. 1146)
- B. Water rinsing
- C. Apply ALODINE 1201

- D. Water rinsing
- F. Drying

The work, after processing and drying, is ready to be painted.

4. Materials:

ALODINE 1201
ALUMIPREP 33

5. Equipment:

Acid resisting (rubber, stainless steel or plastic) buckets, troughs or other suitable containers should be used to hold the ALODINE 1201 or diluted ALODINE 1201 solution. Ordinary steel pails may be used, but only for a short time. Galvanized containers should not be used. If production conditions warrant, troughs may be installed to collect the ALODINE 1201 coating chemical run-off for reuse.

Long handled, window type brushes, clean cloths or synthetic sponges may be used to brush on the ALODINE 1201.

6. Surface Preparation:

Cleaning:

ALUMIPREP 33 is recommended for cleaning. ALUMIPREP 33 is a nonflammable, phosphoric acid based cleaner which produces a chemically clean and corrosion free aluminum surface. Instructions for use of ALUMIPREP 33 are found in Technical Process Bulletin No. 1146.

Water Rinsing:

After cleaning, the metal must be thoroughly rinsed with water. Inadequate rinsing may contaminate an ALODINE 1201 immersion bath or result in a surface condition which may cause corrosion of the finished part.

7. Apply ALODINE 1201:

Buildup:

For brush application, ALODINE 1201 is applied to a chemically cleaned surface using the solution undiluted.

For immersion application, ALODINE 1201 is diluted by mixing 33 parts of ALODINE 1201 and 67 parts of water for each 100 parts of bath volume required.

NOTE: Operators should be equipped with rubber gloves, aprons and goggles to avoid contact with the solution. Adequate ventilation should be provided.

Operation:

Time: 2 minutes to 5 minutes.

Temperature: room temperature to 100° Fahrenheit.

ALODINE 1201 coating chemical should not be allowed to dry on the metal surface. With brush application the surface should be rewet with fresh ALODINE 1201 several times during the treatment time. If drying does occur, rewet with ALODINE 1201 coating chemical prior to water rinsing.

Selecting the size of the area to be treated at one time depends on the method of application, condition of the metal surface, method in which the surface was cleaned, temperature and part configuration.

Colors of the coating produced by ALODINE 1201 will vary from a light gold to a dark tan. Variations in color result from different alloys, metal hardness, metal age, method of cleaning, etc.

Powdering of a chrome conversion coating can result from poor cleaning, drying, over reacting, or for other reasons. Powder can affect paint adhesion. Gently wipe and remove the powder, without abrading the chemical coating, with a dry, clean rag after the work has dried. Caution should be taken not to redeposit oils, lint or other soils back on the aluminum surface.

8. After Treatment:

Water Rinsing:

A thorough rinse with clean water is necessary to remove residual ALODINE 1201 coating chemical salts from the metal surface. Blistering and corrosion problems under paint are often the results of poor rinsing. Chemical salts trapped under a paint film will eventually result in blistering or corrosion problems.

Drying:

As an aid to drying, heating the treated part, blowing off with clean, dry, filtered, forced air or gently wiping with a dry, clean rag will lessen the time required. Do not allow the aluminum metal temperature to exceed 140 Fahrenheit.

Paint soon after the work is dry in order to prevent soils or oxidation from recontaminating the prepared metal surface.

9. Storage Requirements:

ALODINE 1201 coating chemical will freeze at 32° Fahrenheit. It is recommended that the product be stored where freezing will not occur. However, should it freeze, simply thaw it in a warm place and stir it prior to use.

10. Waste Disposal Information:

Applicable regulations concerning disposal and discharge of chemicals should be consulted and followed.

Disposal information for the chemical products used in this process is given on the Material Safety Data Sheet for each product.

The processing bath is acidic and contains hexavalent chromium. Waste treatment and neutralization may be required prior to discharge to sewer.

11. Precautionary Information:

Before handling the chemical products used in the process, the first aid and handling recommendations on the Material Safety Data Sheet for the product should be read, understood and followed.

- * * * * -

®Registered trademark of Henkel Corporation.

Henkel Surface
Technologies
32100 Stephenson
Highway
Madison Heights, MI

"The information presented herein is our interpretation of certain test results and field experience to date. This information is not to be taken as warranty or representation for which we assume legal responsibility, nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your

48071 consideration, investigation and verification." © Henkel Corporation.
Telephone:
248-583-9300
Fax: 248-583-2976

Form Revised 16 May 1997